

Tali Decking

Tali decking is an emerging exterior decking wood in the US, imported from Central and West Africa. It is a preferred decking choice in many European countries.

Tali has an appealing mahogany-like grain character. The wood is photosensitive and darkens with continued exposure to light. Tali is very dense, stable and durable, as well as resistant to fungi, termites, and dry wood borers. The structure of the wood is very uniform without any distinctive markings. It is suitable for exterior use, even untreated.



Ask Us About FSC Certified Tali Decking In Stock.

FSC is a sustainability certification framework based on environmental, social, and economical principles and criteria, with an overall vision of providing current forest product needs without compromising forest health for future generations.



The mark of responsible forestry



Technical Specifications:

Erythrophleum Ivorense

- Janka hardness of 2,920
- Durability Class is the same as Ipe and Cumaru
- Stable, with little movement in service

Sizes:

1 x 4, 1 x 6

5/4 x 4, 5/4 x 6

S4S / E4E

6' to 14' lengths

Custom millwork items available upon request, including railings, accessories, and more.



Decking Materials Comparison Chart

Material	Janka Hardness (MLBF)	Bending Strength (MPSt)	Density (Lbs/CuFt)	Price \$ to \$\$\$\$
Ipe	3.7	25.4	69	\$\$\$\$
Mass	3.2	27.2	66	\$\$\$
Cumaru	3.5	27	68	\$\$\$
Tali	2.9	23.5	56	\$
Tigerwood	2.2	19.6	60	\$\$\$
Garapa	1.6	12.9	54	\$\$
Red Balau	1.6	20.6	53	\$\$\$
Teak	1.2	13.7	40	\$\$\$\$
Kanda	1.2	11.0	70	\$
Composites	1.1	3.0	63	\$\$\$\$
Treated Pine	0.9	12	35	\$

